


Microporous film coated fabric

Silent Coating™



Breathability



Moisture permeation



Windproof



Stretchability



*Differs depending on fabric

A dry, comfortable touch

Microporous wet-type polyurethane film coating keeps the fabric dry even after perspiration, thanks to its high moisture permeability and adequate breathability. Hydrophobic polyurethane is used, meaning the fabric does not deform due to moisture.

Remarkable lightness and stretchability

The extremely thinly coated film maintains the fabric's light weight and stretchability, increasing wearing comfort.




Basic performance

Water resistance	(JIS 1092)	:	300mm~500mm/H ₂ O
Moisture permeability	(JIS L1099-A1)	:	>8,000g/ m ² /24hrs
Breathability	(JIS L1096-A)	:	0.10~2.00 cm ³ / cm ² /sec



微多孔涂层织物

Silent Coating™



透气性



渗潮



防风



弹性



※取决于面料

干燥舒适

这种面料具有微多孔湿式PU涂层，透湿性高，透气性适中，因此即使出汗也能保持衣服内部干燥舒适。使用的是疏水性PU，所以也不会因水分引起变形。

令人吃惊的轻量性和拉伸弹性

通过将涂覆层最大限度地薄膜化，可以在不损坏布料原有的轻量性和拉伸弹性的情况下，给人以舒适的穿着体验。



20

基本性能

防水性	(JIS 1092)	:	300mm~500mm/H
渗潮性	(JIS L1099-A1)	:	>8,000g/ m ² /24hrs
透气性	(JIS L1096-A)	:	0.10~2.00 cm ³ / cm ² /sec

Art in Technology
komatsumateRe

KOMATSU MATERE Co., Ltd.

总公司 - 石川县 能美市 滨町 NU 167番地 TEL:+81-761-55-1111
 东京营业所 - 东京都 港区 南青山 2-5-17 POLA青山大楼 12层 TEL:+81-3-6271-4808
 大阪营业所 - 大阪府 大阪市 北区 梅田 2-2-22 HERBIS ENT 办公楼 8层 TEL:+81-6-6344-4161
 上海代表处 - 中华人民共和国上海市延安西路2201号 上海国际贸易中心 1913室 TEL:+86-21-6275-4558



WEBSITE